



Subham Oils and Resins Pvt Ltd

HO: 183 Bangur Avenue Block B 3rd Floor Kolkata 700055

Works: Surjopur Ishwaripur, Bolgarh Industrial Estate Kalyani Expressway, Kolkata-700121

Technical Data Sheet

AC-39 (Thermosetting Acrylic Resin)

Applications: General Industrial PU

Specifications:

Parameters	Standard Results
Non Volatile Matter (%)	60
Acid Value (mg KOH/g)	<10
Viscosity as such in Gardner Tube (Poise)	35-50 Poise
Color in Gardner	<1
Hydroxyl Value (mg KOH/gm)	70-80

Compatibility:

MF	Compatible
UF	Limited Compatible
Short Oil in Xylene	Compatible
Long Oil in MTO	Not Compatible

Solubility:

Xylene	Complete Solubility
MTO/LAWS	No Solubility
Ethyl Glycol Acetate	Complete Solubility
n-Butyl Acetate	Complete Solubility
Methyl Ethyl Ketone	Complete Solubility

Delivery Forms:-

In 17-19 kgs Metal barrels with following net weight for following percentages:

60% in Xylene/ Ethyl Cellosolve	190 Kgs
---------------------------------	---------