



## Subham Oils and Resins Pvt Ltd

HO: 183 Bangur Avenue Block B 3rd Floor Kolkata 700055

Works: Surjopur Ishwaripur, Bolgarh Industrial Estate Kalyani Expressway, Kolkata-700121

### Technical Data Sheet

### C92X (Fast Drying Alkyd)

**Applications:** Recommended for air drying auto refinishing, Very fast drying time with high gloss car repair and drum coating

**Composition:**

Oil	Approx 33%
Polyol	Penta
Type of Oil	Soya Fatty Acid

**Drying Time:**

Touch Dry	5 mins
Tack Free	60 minutes max
Hard Dry	240 minutes max

**Suggested Mix Drier:**

Lead Octate (24%)	1%
Cobalt Octate (6%)	1%
Zinc Octate (6%)	2%
Calcium Octate(3%)	1%
Magnesium Octate(6%	0.5%
<b>Total</b>	<b>5.5%</b>

**Specifications:**

<b>Parameters</b>	<b>Standard Results</b>
Non Volatile Matter (%)	70
Acid Value (mg KOH/g)	<15
Viscosity in 50% Solution in Xylene at 30°C in Ford Cup B-4	220-250 secs
Color in Gardner	<6

**Solubility:**

Xylene	Complete Solubility
MTO/LAWS	No Solubility
Turpentine	Complete Solubility
n-Butyl Acetate	Complete Solubility
Methyl Ethyl Ketone	Complete Solubility

**Delivery Forms:-**

In 17-19 kgs Metal barrels with following net weight for following percentages:

70% in Xylene	200 Kgs
---------------	---------