



Subham Oils and Resins Pvt Ltd

HO: 183 Bangur Avenue Block B 3rd Floor Kolkata 700055

Works: Surjopur Ishwaripur, Bolgarh Industrial Estate Kalyani Expressway, Kolkata-700121

Technical Data Sheet

CNSL (Cashew Nut Shell Liquid Resin)

Applications: Used for low cost dark shade paints, red oxide primer, tough external durability

Specifications:

Parameters	Standard Results
Non Volatile Matter (%)	70/80/90
Viscosity in 40% Solution in MTO/WS at 30°C in Ford Cup B-4	70-80 secs
Color in Gardner	<12

Drying Time:

Touch Dry	45 mins max
Tack Free	300 mins max
Hard Dry	Overnight

Solubility:

Xylene	Complete Solubility
MTO/LAWS	Complete Solubility
Ethyl Glycol Acetate	Complete Solubility
n-Butyl Acetate	Complete Solubility
Methyl Ethyl Ketone	Complete Solubility

Delivery Forms:-

In 17-19 kgs Metal barrels with following net weight for following percentages:

70/80/90	200 Kgs
----------	---------